

Product information | TECHNICAL DATA SHEET

ANTICORROSIVE ENAMEL PAINT

400 ml, 11.39 Oz, 323 g.

GENERAL DESCRIPTION

Quick drying enamel for direct application on high-gloss oxide. Maintains optimum colour retention when exposed to the outdoors. Ideal for a perfect finish and for saving on antioxidant primer.

FEATURES

- Directly on oxide. Easy to apply and recoat.
- Fast drying.
- Excellent flexibility.
- Does not contain lead or other heavy metals.
- Very good covering power.
- Good anti-corrosion power.
- High resistance to outdoor exposure.
- Durability of brightness and color.
- U.V. Resistant.
- Optimum resistance to scratches once the coating is polymerized.
- Good setting.

APPLICATIONS

Due to the characteristics of the product, we recommend its use for touch-up and painting materials of all kinds.

- Vehicles
- Industrial applications
- Aluminium objects
- DIY
- Plumbing

INSTRUCTIONS FOR USE

- Shake the aerosol well before using, approximately for one minute after hearing the sound of the mixer.
- Apply to clean, dry surfaces. On rusty metallic surfaces, remove rust with a wire brush.
- On plastics and polyesters apply a anchor layer.
- For best results apply in thin layers. Three thin layers are always better than one thick one, and may be repainted within fifteen minutes with the same paint.
- Turn the aerosol upside down to clean out the valve after use. If te nozzle becomes blocked replace it with a new one.
- Never apply to equipment that is plugged in and use in well ventilated areas.
- Request safety datasheets.

PHYSICAL PROPERTIES

Binder type:	Synthetic
Color:	Black, White, Green
Brightness:	<60 %
Dry to the touch (ASTM D-1640 ISO 1517):	25'
Total drying (ASTM D-1640 ISO 1517):	24 h
Thickness of dry layer (ASTM D-823 ISO 2808):	20 µ/layer
Adherencia (ASTM D-3359 ISO 2409):	3B
Salt mist test:	300 h
Theoretical Coverage (pintado en continuo):	2 m ²
Thinner:	Mixture
Vida del producto:	(Well Stored) 5 years
Recoating:	Between 25 mintes and 2 hours. After 48 hours
Painted resistance to heat:	100 °C
Application conditions:	T° environment min 8 °C T° Surface min 5-50 °C Humidity max 85 % R.H.P

*Adherence tests were performed on steel.

IMAGE



LABEL



RAL 1021 EX014PR0993	RAL 6005 EX014PR0992	RAL 9005 EX014PR0991
RAL 2004 EX014PR0994	RAL 9006 EX014PR0990	RAL 9005 Mate / Matte EX014PR0991M
RAL 3000 EX014PR0995	RAL 7016 EX014PR0997	RAL 9010 EX014PR0989
RAL 5010 EX014PR0996		

CAP SYSTEM



Transversal Cap
Trazo biselado - Chiseled line

PACKAGING

Nominal capacity 400 ml.
Heat resistance of packaging: <50 °C
Propellant: DME

Box (6 units)
205 X 140 X 200 mm.

