

Product information | TECHNICAL DATA SHEET

RUST BUSTER

400 ml.

GENERAL DESCRIPTION

High-performance 4-in-1 anti-corrosion spray paint designed to prime, protect against rust, provide high coverage and deliver a durable finish in a single coat. Its direct-to-metal formula can be applied to new or lightly rusted metal surfaces, providing long-lasting corrosion protection for automotive and DIY applications.

FEATURES

- 4-in-1 protection – Primer, anti-corrosion protection, high coverage and topcoat in one product.
- Excellent one-coat coverage
- Direct-to-metal application
- Up to 10-year protection
- For new and lightly rusted metal
- Strong adhesion to multiple surfaces
- Durable finish
- Time-saving application
- Automotive & DIY suitable

APPLICATIONS

Suitable for automotive and general DIY metal applications, including steel and iron components, automotive parts, brackets, frames, gates, fences, railings, gutters, downpipes and other metal surfaces requiring corrosion protection and a durable decorative finish. Apply to clean, dry and properly prepared metal, removing loose rust, dirt, grease and contaminants before application.

INSTRUCTIONS FOR USE

- Shake the aerosol well before using, approximately for one minute after hearing the sound of the mixer.
- Apply to clean, dry surfaces. On rusty metallic surfaces, remove rust with a wire brush.
- On plastics and polyesters apply a anchor layer.
- For best results apply in thin layers. Three thin layers are always better than one thick one, and may be repainted within fifteen minutes with the same paint.
- Turn the aerosol upside down to clean out the valve after use. If te nozzle becomes blocked replace it with a new one.
- Never apply to equipment that is plugged in and use in well ventilated areas.
- Request safety datasheets.

PHYSICAL PROPERTIES

Binder type:	Synthetic
Color:	Gloss White, Gloss Black, Matte Black
Brightness:	<60%
Dry to the touch (ASTM D-1640 ISO 1517):	25'
Total drying (ASTM D-1640 ISO 1517):	24h
Thickness of dry layer (ASTM D-823 ISO 2808):	20 µ/layer
Adhesion (ASTM D-3359 ISO 2409):	3B
Salt mist test:	300 h
Theoretical Coverage (pintado en continuo):	2 m²
Thinner:	Mixture
Shelf life:	(Well Stored) 5 years
Recoating:	Between 25 mintes and 2 hours. After 48 hours
Painted resistance to heat:	100°C
Application conditions:	T° environment min 8°C
	T° Surface min 5-50°C
	Humidity max 85% R.H.P

*Adhesion tests were performed on steel.

150926

IMAGE



LABEL



CAP SYSTEM



Matte Black EX014WR9005M
Gloss Black EX014WR9005
Gloss White EX014WR9010

PACKAGING

Nominal capacity 400 ml.
 Heat resistance of packaging: <50°C
 Propellant: DME

Box (6 units)
 205 X 140 X 200 mm.

